



**S.I.F.R.A. EST S.P.A.**  
 tel.: +39 040 823602  
 Fax: +39 040 280605  
 e-mail: [info@sifraest.com](mailto:info@sifraest.com)  
<http://www.sifraest.com>

## TECHNICAL DATA SHEET

# **SIF-TUBE**® Medical Grade PVC Tube

Product code: **0001T** . . . . . (specific identification code)

Compound: **SIFLEX**® SE0001EG Medical Grade PVC Granulate

**NOTE:** Small color differences depend only on the color tone of the PVC resin.  
 This technical information consists of typical product data and should not be used as a specification.

### CHEMICAL SPECIFICATIONS

Eur. Ph. Ed. in force

#### FORMULATION

- Not less than 55% of poly(vinyl chloride)
- Not more than 40% of di(2-ethylhexyl)phthalate
- Not more than 1% of zin octanoate (zinc 2-ethylhexanoate)
- Not more than 1% of calcium stearate or zinc stearate or 1% of a mixture of the two
- Not more than 1% of *N,N'* diacylethylenediamines (in this context acyl means in particular palmitoyl and stearoyl)
- Not more than 10% of one the following epoxidised oils or 10% of a mixture of the two
- Epoxidised soya oil of which the oxiran oxygen content is 6% to 8% and the iodine value is not greater than 6
- Epoxidised linseed oil of which the oxiran oxygen content is not greater than 10% and the iodine value is not greater than 7

#### TEST

- Alkalinity
- Acidity
- UV absorption
- Reducing Substances
- Water extractable substances
- Appearance

#### Limit Value

- 0,5 HCl 0.01 M
- 0,5 NaOH 0.01 M
- 0,30 230/250nm
- 0,15 251/360nm
- 2.0 ml Na<sub>2</sub>S<sub>2</sub>O<sub>3</sub> 0.01 M
- 1.5 mg
- Clear, colourless

#### GENERAL STATEMENT

We hereby confirm that this product meets the requirements of the European Pharmacopoeia of less than 50 ppm for total incidental Heavy Metals and less than 1.0 ppm for Vinyl chloride.

### BIOLOGICAL REACTIVITY

USP XXIV

#### TEST

- Test for Cytotoxicity
- Acute Systemic injection test in the Mouse
- Intracutaneous Injection in the Rabbit
- Implantation Test in the Rabbit
- Hemolysis test
- Bacterial Endotoxins Test (LAL Test)
- Physicochemical tests
- Plastics

#### VALUE

- In Conformity
- In Conformity
- In Conformity
- In Conformity
- In Conformity
- In Conformity
- In Conformity

### PHYSICAL PROPERTIES

The physical properties listed below are referring to the Compound.

TEST	UNIT MEASURES	VALUE	PROCEDURE
Tensile strength at break	N/cm <sup>2</sup>	1214	ASTM D-638
Elongation at break	%	481	ASTM D-638
Break at low temperature	°C	- 37° C	ASTM D-1043
Shore "A" durometer hardness	SH"A" (15"/48h)	58 ± 2	ISO 868
Density	gr/cm <sup>3</sup>	1,168	ASTM D-792

Date: 20/10/2009 – revision: 07  
 Date of issued: 20/10/09  
 Signature:

Date of verification: 20/10/09  
 Signature:

Date of approval: 20/10/09  
 Signature:

The information contained herein is to our knowledge accurate and reliable as of the date of publication. S.I.F.R.A. EST S.P.A makes no representations as to accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the product for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.